

Nihon Superior SN96Cl Lead-Free Solder Alloy

Category : Metal , Nonferrous Metal , Solder/Braze Alloy , Tin Alloy

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nihon-Superior-SN96Cl-Lead-Free-Solder-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	217 °C	423 °F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	1.0 %	1.0 %	
Silver, Ag	3.8 %	3.8 %	
Tin, Sn	95.2 %	95.2 %	As Remainder

Processing Properties	Metric	English	Comments
Processing Temperature	230 - 235 °C	446 - 455 °F	Reflow Soldering (Peak)
	245 - 255 °C	473 - 491 °F	Wave Soldering

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China