

Nilit FRIANYL A63 HS-GV25 Nylon 6.6 for injection molding, 25% glass fiber reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Nylon 6.6 for injection molding, high impact resistance. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nilit-FRIANYL-A63-HS-GV25-Nylon-66-for-injection-molding-25-glass-fiber-reinforced.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in ³	ISO 1183
Water Absorption	1.5 - 2.5 %	1.5 - 2.5 %	ISO 62
Water Absorption at Saturation	6.0 - 7.0 %	6.0 - 7.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0080 - 0.016 cm/cm	0.0080 - 0.016 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	125 MPa	18100 psi	ISO 2039-1
Tensile Strength at Break	150 MPa	21800 psi	ISO 527
Elongation at Break	6.0 %	6.0 %	ISO 527
Tensile Modulus	6.50 GPa	943 ksi	ISO 527
Flexural Strength	130 MPa	18900 psi	ISO 178
Flexural Modulus	5.40 GPa	783 ksi	ISO 178
Charpy Impact Unnotched	5.50 J/cm ²	26.2 ft-lb/in ²	DIN 53453
	NB	NB	ISO 179/1eU
	4.80 J/cm ²	22.8 ft-lb/in ²	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact, Notched	1.40 J/cm ²	6.66 ft-lb/in ²	DIN 53453
	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Melting Point	256 °C	493 °F	ISO 3146 DSC

Maximum Service Temperature, Air Thermal Properties	110 °C Metric	230 °F English	Continuous; FRISETTA Test Method Comments
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	550 V	550 V	CTI 100; IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China