

Nilit FRIANYL A63 S15 Nylon 6.6 for injection molding

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Impact Grade

Material Notes:

Nylon 6.6 for injection molding, impact modified. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nilit-FRIANYL-A63-S15-Nylon-66-for-injection-molding.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ISO 1183
Water Absorption	1.8 - 2.8 %	1.8 - 2.8 %	ISO 62
Water Absorption at Saturation	7.0 - 8.0 %	7.0 - 8.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.014 - 0.021 cm/cm	0.014 - 0.021 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	110 MPa	16000 psi	ISO 2039-1
Tensile Strength at Break	65.0 MPa	9430 psi	ISO 527
Elongation at Break	30 %	30 %	ISO 527
Tensile Modulus	2.40 GPa	348 ksi	ISO 527
Flexural Strength	60.0 MPa	8700 psi	ISO 178
Flexural Modulus	2.10 GPa	305 ksi	ISO 178
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	NB	NB	DIN 53453
	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	NB	NB	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact, Notched	1.60 J/cm ²	7.61 ft-lb/in ²	DIN 53453
	1.70 J/cm ²	8.09 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	256 °C Metric	493 °F English	ISO 3146 DSC Comments
Maximum Service Temperature, Air	90.0 °C	194 °F	Continuous; FRISETTA Test Method
Deflection Temperature at 0.46 MPa (66 psi)	185 °C	365 °F	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	600 V	600 V	CTI 100; IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China