

Nilit FRIANYL B63 SG30 Nylon 6 for injection molding, 30% mineral filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 30% Mineral Filled

Material Notes:

Nylon 6 for injection molding. Information provided by Frisetta Polymer, which merged into Nilit Plastics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nilit-FRIANYL-B63-SG30-Nylon-6-for-injection-molding-30-mineral-filled.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ISO 1183
Water Absorption	1.5 - 2.5 %	1.5 - 2.5 %	ISO 62
Water Absorption at Saturation	6.0 - 7.0 %	6.0 - 7.0 %	ISO 62
Viscosity Measurement	145	145	Viscosity index; ISO 307
Linear Mold Shrinkage	0.0090 - 0.019 cm/cm	0.0090 - 0.019 in/in	FRISSETTA Test Method

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	150 MPa	21800 psi	ISO 2039-1
Tensile Strength at Break	60.0 MPa	8700 psi	ISO 527
Elongation at Break	30 %	30 %	ISO 527
Tensile Modulus	3.50 GPa	508 ksi	ISO 527
Flexural Strength	85.0 MPa	12300 psi	ISO 178
Flexural Modulus	3.10 GPa	450 ksi	ISO 178
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	NB	NB	DIN 53453
	NB	NB	DIN 53453
	@Temperature -40.0 °C	@Temperature -40.0 °F	
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179/1eA
	1.00 J/cm ²	4.76 ft-lb/in ²	DIN 53453

Thermal Properties	Metric	English	Comments
Melting Point	221 °C	430 °F	ISO 3146 DSC
Maximum Service Temperature, Air	100 °C	212 °F	Continuous; FRISSETTA Test Method

Thermal Properties Deflection Temperature at 0.46 MPa (264 psi)	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	130 °C	266 °F	ISO 75

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 93
Dissipation Factor	0.020 @Frequency 1e+6 Hz	0.020 @Frequency 1e+6 Hz	IEC 250
Comparative Tracking Index	450 V	450 V	CTI 100; IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China