

Nyco NYLITE® Wollastonite in Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Data for polypropylene reinforced with 15% Nyco NYLITE® Wollastonite. Polypropylene used is Braskem TI6200Q High Impact Copolymer 20 MFR -NBWollastonite (calcium metasilicate, or CaSiO_3) is a naturally occurring white, non-metallic mineral with an acicular or needle-shaped crystal structure. This distinctive property makes wollastonite an ideal performance mineral for a broad range of industrial and consumer applications. Information provided by NYCO Minerals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nyco-NYLITE-Wollastonite-in-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in ³	ISO 1183
Filler Content	15 %	15 %	ISO 34351
Moisture Absorption	0.00300 %	0.00300 %	
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	Average
Linear Mold Shrinkage, Flow	0.0070 cm/cm	0.0070 in/in	
Linear Mold Shrinkage, Transverse	0.012 cm/cm	0.012 in/in	
Melt Flow	13 g/10 min @Load 2.16 kg, Temperature 230 °C	13 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength	21.0 MPa	3050 psi	50 mm/min - CH; ISO 527
Elongation at Break	120 %	120 %	50 mm/min - CH; ISO 527
Flexural Strength	28.0 MPa	4060 psi	2 mm/min; ISO 178
Flexural Modulus	2.60 GPa	377 ksi	2 mm/min; ISO 178
Charpy Impact, Notched	0.420 J/cm ² @Temperature -30.0 °C	2.00 ft-lb/in ² @Temperature -22.0 °F	ISO 179
	4.40 J/cm ² @Temperature 23.0 °C	20.9 ft-lb/in ² @Temperature 73.4 °F	ISO 179

Thermal Properties	Metric	English	Comments
	190 µm/m-°C	106 µin/in-°F	

CTE, linear, Parallel to Flow Thermal Properties	Metric @ Temperature -30.0 - 120 °C	English @ Temperature -22.0 - 248 °F	ISO 11359 Comments
CTE, linear, Transverse to Flow	187 µm/m-°C @Temperature -30.0 - 120 °C	104 µin/in-°F @Temperature -22.0 - 248 °F	ISO 11359
Deflection Temperature at 1.8 MPa (264 psi)	57.0 °C	135 °F	ISO 75

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China