

Nye Lubricants 309 (SO) Synthetic Oil

Category : Fluid , Lubricant , Silicone Base

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-309-SO-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Kinematic Viscosity	50 cSt @Temperature 25.0 °C	50 cSt @Temperature 77.0 °F	Base Oil; ASTM D445
Evaporation Loss	0.50 %	0.50 %	24 hrs, 150C; ASTM D972

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	200 °C	392 °F	Recommended
Minimum Service Temperature, Air	-65.0 °C	-85.0 °F	Recommended
Pour Point	-84.0 °C	-119 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	Sil.(Alkyl)	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China