

## Nye Lubricants 5200 (SVLG) Synthetic Oil

Category : Fluid , Lubricant , Multiply-Alkylated Cyclopentane (MAC) , PTFE Gellant

### Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nye-Lubricants-5200-SVLG-Synthetic-Oil.php](http://www.lookpolymers.com/polymer_Nye-Lubricants-5200-SVLG-Synthetic-Oil.php)

| Physical Properties                  | Metric  | English | Comments                                |
|--------------------------------------|---------|---------|-----------------------------------------|
| Viscosity Measurement                | 137     | 137     | Viscosity Index of Base Oil; ASTM D2270 |
| Kinematic Viscosity at 40°C (104°F)  | 108 cSt | 108 cSt | Base Oil; ASTM D445                     |
| Kinematic Viscosity at 100°C (212°F) | 15 cSt  | 15 cSt  | Base Oil; ASTM D445                     |
| Evaporation Loss                     | 0.10 %  | 0.10 %  | 168 hrs, 100C; ASTM D972                |

| Mechanical Properties      | Metric | English | Comments                      |
|----------------------------|--------|---------|-------------------------------|
| Penetration P(0), 1/10 mm  | 320    | 320     | ASTM D217                     |
| Penetration P(60), 1/10 mm | 323    | 323     | ASTM D217                     |
| Oil Separation             | 4.0 %  | 4.0 %   | 24 hrs, 100C; FTM 719B, 321.2 |

| Thermal Properties               | Metric   | English  | Comments           |
|----------------------------------|----------|----------|--------------------|
| Maximum Service Temperature, Air | 125 °C   | 257 °F   | Recommended        |
| Minimum Service Temperature, Air | -45.0 °C | -49.0 °F | Recommended        |
| Pour Point                       | -55.0 °C | -67.0 °F | Base Oil; ASTM D97 |

| Descriptive Properties | Value    | Comments |
|------------------------|----------|----------|
| Base Fluid Type        | Pennzane |          |
| Gellant Type           | PTFE     |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China