

Nye Lubricants 738 (RL) Synthetic Oil

Category : Fluid , Lubricant , Clay Gellant , Polyalphaolefin (PAO)

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-738-RL-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Kinematic Viscosity at 40°C (104°F)	29 cSt	29 cSt	Base Oil; ASTM D445

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	400	400	ASTM D217
Penetration P(60), 1/10 mm	>= 400	>= 400	ASTM D217

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 °C	248 °F	Recommended
Minimum Service Temperature, Air	-54.0 °C	-65.2 °F	Recommended
Pour Point	-65.0 °C	-85.0 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	PAO	
Gellant Type	Clay	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China