

Nye Lubricants 798 (RL) Synthetic Oil

Category : Fluid , Lubricant , Lithium Gellant , Organic Soap Gellant , Synthetic Ether Base

Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Nye-Lubricants-798-RL-Synthetic-Oil.php

Physical Properties	Metric	English	Comments
Viscosity Measurement	142	142	Viscosity Index of Base Oil; ASTM D2270
Kinematic Viscosity at 40°C (104°F)	57 cSt	57 cSt	Base Oil; ASTM D445
Kinematic Viscosity at 100°C (212°F)	9.0 cSt	9.0 cSt	Base Oil; ASTM D445
Evaporation Loss	0.10 %	0.10 %	24 hrs, 100C; ASTM D972

Mechanical Properties	Metric	English	Comments
Penetration P(0), 1/10 mm	228	228	ASTM D217
Penetration P(60), 1/10 mm	249	249	ASTM D217
Oil Separation	0.20 %	0.20 %	24 hrs, 100C; FTM 719B, 321.2

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	Recommended
Minimum Service Temperature, Air	-40.0 °C	-40.0 °F	Recommended
Pour Point	-57.0 °C	-70.6 °F	Base Oil; ASTM D97

Descriptive Properties	Value	Comments
Base Fluid Type	Ester(PE)	
Gellant Type	Li soap	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China