

## Nye Lubricants UniFlor 8771R (UF) Synthetic Oil

Category : Fluid , Lubricant , Perfluoropolyether (PFPE) , PTFE Gellant

### Material Notes:

Information provided by Nye Lubricants.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nye-Lubricants-UniFlor-8771R-UF-Synthetic-Oil.php](http://www.lookpolymers.com/polymer_Nye-Lubricants-UniFlor-8771R-UF-Synthetic-Oil.php)

| Physical Properties                  | Metric  | English | Comments                                |
|--------------------------------------|---------|---------|-----------------------------------------|
| Viscosity Measurement                | 231     | 231     | Viscosity Index of Base Oil; ASTM D2270 |
| Kinematic Viscosity at 40°C (104°F)  | 192 cSt | 192 cSt | Base Oil; ASTM D445                     |
| Kinematic Viscosity at 100°C (212°F) | 35 cSt  | 35 cSt  | Base Oil; ASTM D445                     |
| Evaporation Loss                     | 0.00 %  | 0.00 %  | 24 hrs, 100C; ASTM D972                 |

| Mechanical Properties      | Metric | English | Comments                      |
|----------------------------|--------|---------|-------------------------------|
| Penetration P(0), 1/10 mm  | 269    | 269     | ASTM D217                     |
| Penetration P(60), 1/10 mm | 285    | 285     | ASTM D217                     |
| Oil Separation             | 5.8 %  | 5.8 %   | 24 hrs, 100C; FTM 719B, 321.2 |

| Thermal Properties               | Metric   | English  | Comments           |
|----------------------------------|----------|----------|--------------------|
| Maximum Service Temperature, Air | 250 °C   | 482 °F   | Recommended        |
| Minimum Service Temperature, Air | -50.0 °C | -58.0 °F | Recommended        |
| Pour Point                       | -53.0 °C | -63.4 °F | Base Oil; ASTM D97 |

| Descriptive Properties | Value     | Comments |
|------------------------|-----------|----------|
| Base Fluid Type        | PFPE(lin) |          |
| Gellant Type           | PTFE      |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China