

## Nylene® 601 Nylon 6, Extrusion Grade

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Extruded

### Material Notes:

Dry as molded. Extrusion grade. Nylene 601 is the heat stabilized version of 600 which is a general purpose, medium viscosity, extrusion grade resin used in applications such as rods, slabs, and tubing. Other applications include wire jacketing and centrifugal casting which require good dielectric properties, toughness, and fatigue resistance. Optimum processing conditions should provide a melt temperature of 480 - 500°F at the die. ALM, Nylene Canada, and Custom Resins are all operating companies of Polymeric Resources Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Nylene-601-Nylon-6-Extrusion-Grade.php](http://www.lookpolymers.com/polymer_Nylene-601-Nylon-6-Extrusion-Grade.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.9 %	1.9 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	83.0 MPa	12000 psi	ASTM D638
Elongation at Break	70 %	70 %	ASTM D638
Flexural Yield Strength	102 MPa	14800 psi	ASTM D790
Izod Impact, Notched	0.400 J/cm	0.749 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	175 °C	347 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	75.0 °C	167 °F	ASTM D648
Flammability, UL94	V-2	V-2	

Processing Properties	Metric	English	Comments
Processing Temperature	255 °C	491 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China