

Outokumpu 4406 Cr-Ni-Mo Austenitic Stainless Steel

Category : Metal , Ferrous Metal , Austenitic , Stainless Steel

Material Notes:

Applications: Wet corrosion resistance and general service. Available in hot rolled plate (Quarto), hot rolled strip/sheet (CPP), cold rolled strip/sheet, cold rolled narrow strip, bar, and rod forms.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Outokumpu-4406-Cr-Ni-Mo-Austenitic-Stainless-Steel.php

Physical Properties	Metric	English	Comments
Density	8.00 g/cc	0.289 lb/in ³	RT

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	620 MPa	89900 psi	Outokumpu Typical, Hot Rolled Plate (Quarto); EN 10002-1
	440 MPa	63800 psi	EN min.; EN 10002-5
	@Temperature 300 °C	@Temperature 572 °F	
	460 MPa	66700 psi	EN min.; EN 10002-5
	@Temperature 200 °C	@Temperature 392 °F	
	520 MPa	75400 psi	EN min.; EN 10002-5
Tensile Strength, Yield	@Temperature 100 °C	@Temperature 212 °F	
	800 MPa	116000 psi	EN min; EN 10002-5
	@Temperature -80.0 °C	@Temperature -112 °F	
	1150 MPa	167000 psi	EN min; EN 10002-5
	@Temperature -196 °C	@Temperature -321 °F	
	280 MPa	40600 psi	EN min.,RT; EN 10002-1
Tensile Strength, Yield	@Strain 0.200 %	@Strain 0.200 %	
	320 MPa	46400 psi	Outokumpu Typical,Hot Rolled Plate (Quarto); EN 10002-1
	@Strain 0.200 %	@Strain 0.200 %	
	360 MPa	52200 psi	Outokumpu Typical,Hot Rolled Plate (Quarto); EN 10002-1
	@Strain 1.00 %	@Strain 1.00 %	
	128 MPa	18600 psi	EN min.; EN 10002-5
Tensile Strength, Yield	@Strain 0.200 %, Temperature 500 °C	@Strain 0.200 %, Temperature 932 °F	
	135 MPa	19600 psi	

Mechanical Properties	Metric	English	EN min.; EN 10002-5
	@Strain 0.200 %, Temperature 400 °C	@Strain 0.200 %, Temperature 752 °F	
	145 MPa	21000 psi	EN min.; EN 10002-5
	@Strain 0.200 %, Temperature 300 °C	@Strain 0.200 %, Temperature 572 °F	
	158 MPa	22900 psi	EN min.; EN 10002-5
	@Strain 1.00 %, Temperature 500 °C	@Strain 1.00 %, Temperature 932 °F	
	164 MPa	23800 psi	EN min.; EN 10002-5
	@Strain 1.00 %, Temperature 400 °C	@Strain 1.00 %, Temperature 752 °F	
	167 MPa	24200 psi	EN min.; EN 10002-5
	@Strain 0.200 %, Temperature 200 °C	@Strain 0.200 %, Temperature 392 °F	
	175 MPa	25400 psi	EN min.; EN 10002-5
	@Strain 1.00 %, Temperature 300 °C	@Strain 1.00 %, Temperature 572 °F	
	198 MPa	28700 psi	EN min.; EN 10002-5
	@Strain 1.00 %, Temperature 200 °C	@Strain 1.00 %, Temperature 392 °F	
	211 MPa	30600 psi	EN min.; EN 10002-5
	@Strain 0.200 %, Temperature 100 °C	@Strain 0.200 %, Temperature 212 °F	
	246 MPa	35700 psi	EN min.; EN 10002-5
	@Strain 1.00 %, Temperature 100 °C	@Strain 1.00 %, Temperature 212 °F	
	380 MPa	55100 psi	EN min.; EN 10002-5
	@Strain 0.200 %, Temperature -80.0 °C	@Strain 0.200 %, Temperature -112 °F	
	450 MPa	65300 psi	EN min.; EN 10002-5
	@Strain 1.00 %, Temperature -80.0 °C	@Strain 1.00 %, Temperature -112 °F	
	600 MPa	87000 psi	EN min.; EN 10002-5
	@Strain 0.200 %, Temperature -196 °C	@Strain 0.200 %, Temperature -321 °F	
	700 MPa	102000 psi	EN min.; EN 10002-5
	@Strain 1.00 %, Temperature -196 °C	@Strain 1.00 %, Temperature -321 °F	

Mechanical Properties	Metric	English	Comments
Elongation at Break	30 %	30 %	Typical, Hot Rolled Plate (Quarto), EN 10002-1
	@Temperature -196 °C	@Temperature -321 °F	EN min
	35 %	35 %	EN min
	@Temperature -80.0 °C	@Temperature -112 °F	
Modulus of Elasticity	200 GPa	29000 ksi	RT
	165 GPa	23900 ksi	
	@Temperature 500 °C	@Temperature 932 °F	
	172 GPa	24900 ksi	
	@Temperature 400 °C	@Temperature 752 °F	
	179 GPa	26000 ksi	
	@Temperature 300 °C	@Temperature 572 °F	
	186 GPa	27000 ksi	
	@Temperature 200 °C	@Temperature 392 °F	
	194 GPa	28100 ksi	
	@Temperature 100 °C	@Temperature 212 °F	
Poissons Ratio	0.30	0.30	RT
Shear Modulus	77.0 GPa	11200 ksi	calculated
Impact Test	>= 60.0 J	>= 44.3 ft-lb	Hot rolled plate/Cold rolled strip/sheet, 10x10mm test pieces; EN 10045-1

Thermal Properties	Metric	English	Comments
CTE, linear	16.0 µm/m-°C	8.89 µin/in-°F	
	@Temperature 100 °C	@Temperature 212 °F	
	17.5 µm/m-°C	9.72 µin/in-°F	
	@Temperature 400 °C	@Temperature 752 °F	
Specific Heat Capacity	0.500 J/g-°C	0.120 BTU/lb-°F	RT
Thermal Conductivity	15.0 W/m-K	104 BTU-in/hr-ft²-°F	RT
	20.0 W/m-K	139 BTU-in/hr-ft²-°F	
	@Temperature 400 °C	@Temperature 752 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.020 %	0.020 %	
Chromium, Cr	17.2 %	17.2 %	
Iron, Fe	70.24 %	70.24 %	
Molybdenum, Mo	2.1 %	2.1 %	
Nickel, Ni	10.3 %	10.3 %	
Nitrogen, N	0.14 %	0.14 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000750 ohm-cm	0.0000750 ohm-cm	RT

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China