

Overview of materials for Nylon 612 with PTFE Filler

Category : Polymer , Thermoplastic , Nylon , Nylon 612 , Nylon 612 with PTFE Filler

Material Notes:

This property data is a summary of similar materials in the MatWeb database for the category "Nylon 612 with PTFE Filler". Each property range of values reported is minimum and maximum values of appropriate MatWeb entries. The comments report the average value, and number of data points used to calculate the average. The values are not necessarily typical of any specific grade, especially less common values and those that can be most affected by additives or processing methods.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Overview-of-materials-for-Nylon-612-with-PTFE-Filler.php

Physical Properties	Metric	English	Comments
Density	1.12 - 1.37 g/cc	0.0405 - 0.0495 lb/in ³	Average value: 1.19 g/cc Grade Count:15
Water Absorption	0.140 - 0.500 %	0.140 - 0.500 %	Average value: 0.274 % Grade Count:7
Linear Mold Shrinkage	0.00200 - 0.0400 cm/cm	0.00200 - 0.0400 in/in	Average value: 0.0180 cm/cm Grade Count:15

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109 - 121	109 - 121	Average value: 116 Grade Count:5
Tensile Strength, Ultimate	44.8 - 131 MPa	6500 - 19000 psi	Average value: 55.4 MPa Grade Count:15
Elongation at Break	2.00 - 30.0 %	2.00 - 30.0 %	Average value: 9.07 % Grade Count:15
Modulus of Elasticity	1.86 - 8.96 GPa	270 - 1300 ksi	Average value: 2.71 GPa Grade Count:14
Flexural Yield Strength	62.1 - 200 MPa	9000 - 29000 psi	Average value: 79.9 MPa Grade Count:14
Flexural Modulus	1.72 - 7.58 GPa	250 - 1100 ksi	Average value: 2.46 GPa Grade Count:14
Izod Impact, Notched	0.427 - 1.07 J/cm	0.800 - 2.00 ft-lb/in	Average value: 0.532 J/cm Grade Count:15
Izod Impact, Unnotched	3.20 - 12.8 J/cm	6.00 - 24.0 ft-lb/in	Average value: 6.45 J/cm Grade Count:13

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	121 - 218 °C	250 - 425 °F	Average value: 183 °C Grade Count:6
Deflection Temperature at 1.8 MPa (264 psi)	74.0 - 216 °C	165 - 420 °F	Average value: 96.5 °C Grade Count:13
Flammability, UL94	HB	HB	Grade Count:11

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+13 - 1.00e+15 ohm-cm	1.00e+13 - 1.00e+15 ohm-cm	Average value: 2.26e+14 ohm-cm Grade Count:5

Processing Properties	Metric	English	Comments
Processing Temperature	252 - 279 °C	485 - 535 °F	Average value: 266 °C Grade Count:6
Melt Temperature	232 - 285 °C	450 - 545 °F	Average value: 263 °C Grade Count:8
Mold Temperature	49.0 - 107 °C	120 - 225 °F	Average value: 77.5 °C Grade Count:14
Drying Temperature	79.4 - 107 °C	175 - 225 °F	Average value: 82.3 °C Grade Count:8
Moisture Content	0.200 %	0.200 %	Average value: 0.200 % Grade Count:6
Dew Point	-17.8 °C	0.000 °F	Average value: -17.8 °C Grade Count:6
Injection Pressure	68.9 - 124 MPa	10000 - 18000 psi	Average value: 96.5 MPa Grade Count:12

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China