

Oxford Polymers 30GF-25PTFE 30% Glass Fiber/PTFE Reinforced Polyphenylene Sulfide (discontinued **)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS) , Polyphenylene Sulfide (PPS), PTFE/Glass-Fiber Filled

Material Notes:

30% Glass Fiber/PTFE Reinforced Polyphenylene Sulfide Information provided by Oxford Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Oxford-Polymers-30GF-25PTFE-30-Glass-FiberPTFE-Reinforced-Polyphenylene-Sulfide-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.66 g/cc	1.66 g/cc	ASTM D792
Filler Content	30 %	30 %	
Water Absorption	0.020 %	0.020 %	ASTM D570
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	131 MPa	19000 psi	ASTM D638
Elongation at Break	1.5 %	1.5 %	ASTM D638
Flexural Strength	186 MPa	27000 psi	ASTM D790
Flexural Modulus	11.0 GPa	1600 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm @Temperature 23.0 °C	1.40 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China