

Oxford Polymers 30GF 30% Glass Fiber Filled Polyetherimide for Extrusion and Injection Molding

Category : Polymer , Thermoplastic , Polyetherimide (PEI) , Polyetherimide (PEI), 30% Glass Fiber

Material Notes:

30% Glass Fiber Filled Polyetherimide for Extrusion and Injection Molding Information provided by Oxford Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Oxford-Polymers-30GF-30-Glass-Fiber-Filled-Polyetherimide-for-Extrusion-and-Injection-Molding.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
Filler Content	30 %	30 %	
Water Absorption	0.16 %	0.16 %	ASTM D570
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	155 MPa	22500 psi	ASTM D638
Elongation at Break	2.3 %	2.3 %	ASTM D638
Tensile Modulus	8.27 GPa	1200 ksi	ASTM D638
Flexural Strength	207 MPa	30000 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Izod Impact, Notched	0.961 J/cm @Temperature 23.0 °C	1.80 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	212 °C	414 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ASTM D648

Processing Properties	Metric	English	Comments
Processing Temperature	382 °C	720 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China