

Oxford Polymers 901-BK Polycarbonate/Polyetherimide Alloy

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polyetherimide (PEI)

Material Notes:

Polycarbonate/Polyetherimide Alloy Information provided by Oxford Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Oxford-Polymers-901-BK-PolycarbonatePolyetherimide-Alloy.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ASTM D792
Water Absorption	0.25 %	0.25 %	ASTM D570
Linear Mold Shrinkage	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	100 MPa	14500 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	145 MPa	21000 psi	ASTM D790
Flexural Modulus	3.28 GPa	475 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm @Temperature 23.0 °C	1.40 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	182 °C	360 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China