

PEAK Werkstoff DISPAL S220 Aluminum Alloy, AlSi35, Condition O

Category : Metal , Nonferrous Metal , Aluminum Alloy

Material Notes:

Excellent properties:abrasive stabilityhigh stiffness (E-modulus)resistance even at high temperaturesgood grindabilityPEAK DISPAL materials allow the manufacturing of pistons for highest operational demands.Information provided by PEAK Werkstoff GmbH

Order this product through the following link:

http://www.lookpolymers.com/polymer_PEAK-Werkstoff-DISPAL-S220-Aluminum-Alloy-AlSi35-Condition-O.php

Physical Properties	Metric	English	Comments
Density	2.413 - 2.667 g/cc	0.08718 - 0.09635 lb/in³	

Mechanical Properties	Metric	English	Comments
Hardness, Vickers	>= 58	>= 58	
Tensile Strength at Break	>= 140 MPa	>= 20300 psi	
Tensile Strength, Yield	>= 80.0 MPa	>= 11600 psi	
Elongation at Break	>= 2.0 %	>= 2.0 %	
Modulus of Elasticity	>= 80.0 GPa	>= 11600 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	14.6 - 15.6 µm/m-°C	8.11 - 8.67 µin/in-°F	
	@Temperature 20.0 - 100 °C	@Temperature 68.0 - 212 °F	
	15.5 - 16.5 µm/m-°C	8.61 - 9.17 µin/in-°F	
	@Temperature 20.0 - 200 °C	@Temperature 68.0 - 392 °F	
	16.3 - 17.3 µm/m-°C	9.06 - 9.61 µin/in-°F	
	@Temperature 20.0 - 300 °C	@Temperature 68.0 - 572 °F	
Specific Heat Capacity	0.830 - 0.870 J/g-°C	0.198 - 0.208 BTU/lb-°F	
Thermal Conductivity	123.5 W/m-K	857.1 BTU-in/hr-ft²-°F	
	@Temperature 400 °C	@Temperature 752 °F	
	131 W/m-K	909 BTU-in/hr-ft²-°F	
	@Temperature 300 °C	@Temperature 572 °F	

Thermal Properties	136.8 W/m-K Metric	949.4 BTU-in/hr-ft ² -°F English	Comments
	@Temperature 200 °C	@Temperature 392 °F	
	144.3 W/m-K	1001 BTU-in/hr-ft ² -°F	
	@Temperature 100 °C	@Temperature 212 °F	
	152.4 W/m-K	1058 BTU-in/hr-ft ² -°F	
	@Temperature 30.0 °C	@Temperature 86.0 °F	
Melting Point	573 - 881 °C	1060 - 1620 °F	
Solidus	572.9 - 578.9 °C	1063 - 1074 °F	
Liquidus	875.3 - 881.3 °C	1608 - 1618 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	65 %	65 %	As Balance
Silicon, Si	35 %	35 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000620 - 0.00000660 ohm-cm	0.00000620 - 0.00000660 ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China