

PTS Trimid® N6-200L Nylon 6 with Lube

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_PTS-Trimid-N6-200L-Nylon-6-with-Lube.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Water Absorption	1.6 %	1.6 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	85.5 MPa	12400 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Flexural Modulus	2.83 GPa	410 ksi	ASTM D790
Izod Impact, Notched	0.640 J/cm @Thickness 3.17 mm	1.20 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	216 °C	421 °F	ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	174 °C	345 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	63.0 °C	145 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	<= 216 °C	<= 420 °F	
Middle Barrel Temperature	227 - 254 °C	440 - 490 °F	
Front Barrel Temperature	238 - 266 °C	460 - 510 °F	
Nozzle Temperature	238 - 266 °C	460 - 510 °F	
Melt Temperature	232 - 271 °C	450 - 520 °F	
Mold Temperature	21.1 - 93.3 °C	70.0 - 200 °F	
Drying Temperature	82.2 °C	180 °F	

Dry Time Processing Properties	3 - 4 hour Metric	3 - 4 hour English	Comments
Injection Pressure	82.7 - 172 MPa	12000 - 25000 psi	
Back Pressure	0.000 - 0.345 MPa	0.000 - 50.0 psi	
Screw Speed	40 - 80 rpm	40 - 80 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China