

PTS Trimid® N6-M200HL Impact Modified Heat Stabilized Nylon 6 with Lube

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Heat Stabilized

Material Notes:

Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_PTS-Trimid-N6-M200HL-Impact-Modified-Heat-Stabilized-Nylon-6-with-Lube.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	37.9 MPa	5500 psi	ASTM D638
Tensile Strength, Yield	55.8 MPa	8090 psi	ASTM D638
Elongation at Break	80 %	80 %	ASTM D638
Flexural Yield Strength	75.8 MPa	11000 psi	ASTM D790
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Notched	1.28 J/cm @Thickness 3.17 mm	2.40 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	216 °C	421 °F	ASTM D789

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	138 - 216 °C	280 - 420 °F	
Middle Barrel Temperature	227 - 254 °C	440 - 490 °F	
Front Barrel Temperature	238 - 266 °C	460 - 510 °F	
Nozzle Temperature	238 - 266 °C	460 - 510 °F	
Melt Temperature	232 - 271 °C	450 - 520 °F	
Mold Temperature	21.1 - 93.3 °C	70.0 - 200 °F	
Drying Temperature	82.2 °C	180 °F	
Dry Time	3 - 4 hour	3 - 4 hour	
Injection Pressure	82.7 - 172 MPa	12000 - 25000 psi	
Back Pressure	0.000 - 0.345 MPa	0.000 - 50.0 psi	
Screw Speed	40 - 80 rpm	40 - 80 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China