

Park Electrochemical Nelcote® E-766B Epoxy Prepreg, 7581 E-Glass Reinforced

Category : Polymer , Thermoset , Epoxy

Material Notes:

Nelcote® E-766B is a low tack, self adhesive epoxy resin system designed for honeycomb applications. E-766B displays excellent peel properties. Key Features and Benefits: Self adhesive resin system for sandwich panel applications Flame retardant and self-extinguishing Low tack and long out-times for ease of processing Applications/Qualifications: Sandwich panels / structures Aircraft Interiors Mass Transit Interiors Information provided by Park Electrochemical Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Park-Electrochemical-Nelcote-E-766B-Epoxy-Prepreg-7581-E-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Volatiles	<= 1.0 % @Temperature 163 °C	<= 1.0 % @Temperature 325 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	448 MPa @Temperature 23.9 °C	65000 psi @Temperature 75.0 °F	ASTM D3039
Tensile Modulus	21.4 GPa @Temperature 23.9 °C	3100 ksi @Temperature 75.0 °F	Dry; ASTM D3039
Compressive Strength	448 MPa @Temperature 23.9 °C	65000 psi @Temperature 75.0 °F	Dry; ASTM D695
Compressive Modulus	22.1 GPa @Temperature 23.9 °C	3200 ksi @Temperature 75.0 °F	Dry; ASTM D695
Shear Strength	53.8 MPa @Temperature 23.9 °C	7800 psi @Temperature 75.0 °F	Short-Beam, Dry; ASTM D2344

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	93.0 °C	199 °F	Dry; DMA

Processing Properties	Metric	English	Comments
Shelf Life	12.0 Month @Temperature -17.8 °C	12.0 Month @Temperature 0.000 °F	

Descriptive Properties	Value	Comments
Fabric Area Weight (g/m ²)	300	
Prepreg Resin Content (%)	37-43	
Resin Flow (%)	15-21	275°F, 15psi

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China