

Parker Chomerics CHO-MUTE 9005 Microwave Absorber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

Material Notes:

Microwave Absorber Material. Elastomer microwave absorber is designed to offer wide band attenuation within operating frequencies of 500 MHz to 18 GHz. CHO-MUTE 9005 incorporates a high tech silicone polymer system that offers the benefit of wide band absorption and high permeability in a lightweight and flexible product form. Typical Applications: Hand held electronics; Wireless voice or data telecommunication; Military electronics; GPS; Ruggedized computers; Night vision and Telecommunication infrastructure equipment. Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-CHO-MUTE-9005-Microwave-Absorber.php

Physical Properties	Metric	English	Comments
Specific Gravity	3.40 g/cc	3.40 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	ASTM D2240
Tensile Strength at Break	3.45 MPa	500 psi	ASTM D412
Elongation at Break	>= 200 %	>= 200 %	ASTM D412
Tear Strength	10.5 kN/m	59.9 pli	ASTM D624

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.560 W/m-K	3.89 BTU-in/hr-ft ² -°F	ASTM D5470
Maximum Service Temperature, Air	160 °C	320 °F	
Minimum Service Temperature, Air	-50.0 °C	-58.0 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+6 ohm-cm	>= 1.00e+6 ohm-cm	Bulk, Initial; CEPS-0002
Surface Resistivity per Square	>= 1.00e+6 ohm	>= 1.00e+6 ohm	Initial; CEPS-0002
Magnetic Permeability	1.76	1.76	ASTM D2520
Shielding Effectiveness	-23.0 dB	-23.0 dB	Microwave Absorption
	@Thickness 1.57 mm, Frequency 8.00e+9 Hz	@Thickness 0.0620 in, Frequency 8.00e+9 Hz	
	-21.0 dB	-21.0 dB	Microwave Absorption
	@Thickness 2.36 mm,	@Thickness 0.0930 in,	

Electrical Properties	Frequency 6.00e+9 Hz Metric	Frequency 6.00e+9 Hz English	Comments
	-15.0 dB	-15.0 dB	
	@Thickness 1.57 mm, Frequency 1.05e+10 Hz	@Thickness 0.0620 in, Frequency 1.05e+10 Hz	Microwave Absorption
	-10.0 dB	-10.0 dB	
	@Thickness 1.57 mm, Frequency 1.55e+10 Hz	@Thickness 0.0620 in, Frequency 1.55e+10 Hz	Microwave Absorption
	-8.00 dB	-8.00 dB	
	@Thickness 0.813 mm, Frequency 1.55e+10 Hz	@Thickness 0.0320 in, Frequency 1.55e+10 Hz	Microwave Absorption
	-7.00 dB	-7.00 dB	
	@Thickness 2.36 mm, Frequency 1.05e+10 Hz	@Thickness 0.0930 in, Frequency 1.05e+10 Hz	Microwave Absorption
	-7.00 dB	-7.00 dB	
	@Thickness 2.36 mm, Frequency 1.55e+10 Hz	@Thickness 0.0930 in, Frequency 1.55e+10 Hz	Microwave Absorption
	-7.00 dB	-7.00 dB	
	@Thickness 1.57 mm, Frequency 5.00e+9 Hz	@Thickness 0.0620 in, Frequency 5.00e+9 Hz	Microwave Absorption
	-7.00 dB	-7.00 dB	
	@Thickness 1.57 mm, Frequency 5.50e+9 Hz	@Thickness 0.0620 in, Frequency 5.50e+9 Hz	Microwave Absorption
	-6.00 dB	-6.00 dB	
	@Thickness 0.508 mm, Frequency 1.55e+10 Hz	@Thickness 0.0200 in, Frequency 1.55e+10 Hz	Microwave Absorption
	-6.00 dB	-6.00 dB	
	@Thickness 3.17 mm, Frequency 1.55e+10 Hz	@Thickness 0.125 in, Frequency 1.55e+10 Hz	Microwave Absorption
	-5.00 dB	-5.00 dB	
	@Thickness 3.17 mm, Frequency 5.50e+9 Hz	@Thickness 0.125 in, Frequency 5.50e+9 Hz	Microwave Absorption
	-5.00 dB	-5.00 dB	
	@Thickness 3.17 mm, Frequency 1.05e+10 Hz	@Thickness 0.125 in, Frequency 1.05e+10 Hz	Microwave Absorption
	-5.00 dB	-5.00 dB	
	@Thickness 0.508 mm, Frequency 1.05e+10 Hz	@Thickness 0.0200 in, Frequency 1.05e+10 Hz	Microwave Absorption
	-4.00 dB	-4.00 dB	

Electrical Properties	Metric	English	Comments
	@Thickness 0.813 mm, Frequency 5.50e+9 Hz	@Thickness 0.0320 in, Frequency 5.50e+9 Hz	
	-3.00 dB	-3.00 dB	
	@Thickness 1.57 mm, Frequency 2.00e+8 Hz	@Thickness 0.0620 in, Frequency 2.00e+8 Hz	Microwave Absorption
	-3.00 dB	-3.00 dB	
	@Thickness 0.508 mm, Frequency 5.50e+9 Hz	@Thickness 0.0200 in, Frequency 5.50e+9 Hz	Microwave Absorption
	-3.00 dB	-3.00 dB	
	@Thickness 2.36 mm, Frequency 2.00e+9 Hz	@Thickness 0.0930 in, Frequency 2.00e+9 Hz	Microwave Absorption
	-3.00 dB	-3.00 dB	
	@Thickness 0.254 mm, Frequency 1.55e+10 Hz	@Thickness 0.0100 in, Frequency 1.55e+10 Hz	Microwave Absorption
	-2.00 dB	-2.00 dB	
	@Thickness 0.254 mm, Frequency 1.05e+10 Hz	@Thickness 0.0100 in, Frequency 1.05e+10 Hz	Microwave Absorption
	-0.500 dB	-0.500 dB	
	@Thickness 0.254 mm, Frequency 5.50e+9 Hz	@Thickness 0.0100 in, Frequency 5.50e+9 Hz	Microwave Absorption
	0.00 dB	0.00 dB	
	@Thickness 0.508 mm, Frequency 5.00e+8 Hz	@Thickness 0.0200 in, Frequency 5.00e+8 Hz	Microwave Absorption
	0.00 dB	0.00 dB	
	@Thickness 2.36 mm, Frequency 5.00e+8 Hz	@Thickness 0.0930 in, Frequency 5.00e+8 Hz	Microwave Absorption
	0.00 dB	0.00 dB	
	@Thickness 0.254 mm, Frequency 5.00e+8 Hz	@Thickness 0.0100 in, Frequency 5.00e+8 Hz	Microwave Absorption
	0.00 dB	0.00 dB	
	@Thickness 3.17 mm, Frequency 5.00e+8 Hz	@Thickness 0.125 in, Frequency 5.00e+8 Hz	Microwave Absorption
	0.00 dB	0.00 dB	
	@Thickness 0.813 mm, Frequency 5.00e+8 Hz	@Thickness 0.0320 in, Frequency 5.00e+8 Hz	Microwave Absorption
	0.00 dB	0.00 dB	
	@Thickness 1.57 mm, Frequency 5.00e+8 Hz	@Thickness 0.0620 in, Frequency 5.00e+8 Hz	Microwave Absorption

Electrical Properties	Metric	English	Comments
Dielectric Loss Index	0.15	0.15	ASTM D2520

Descriptive Properties	Value	Comments
Composition	Ferrous filled silicone	
Magnetic Loss Tangent	0.602	ASTM D2520

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China