

Parker Chomerics CHO-SEAL® 0862 Conductive Elastomer

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE) , Silicone

Material Notes:

Description: Low-end shielding and ESD protection; high tensile strength; no corrosion or fluid resistance.Extruded onlyRoHS

CompliantInformation provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-CHO-SEAL-0862-Conductive-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 - 1.50 g/cc	0.900 - 1.50 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65 - 75	65 - 75	ASTM D2240
Tensile Strength	>= 4.14 MPa	>= 600 psi	ASTM D412
Elongation at Break	>= 100 %	>= 100 %	ASTM D412
Tear Strength	<= 10.5 kN/m	<= 60.0 pli	ASTM D624

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	351 °F	
Minimum Service Temperature, Air	-51.0 °C	-59.8 °F	Flex TR10
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	<= 24 ohm-cm	<= 24 ohm-cm	without pressure-sensitive adhesive; CEPS-0002

Descriptive Properties	Value	Comments
Binder	Silicone	
Filler	Carbon	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China