

Parker Chomerics Tecknit Teckfip™ HC FIP-C Formed in Place Conductive Elastomer

Category : Polymer

Material Notes:

Description: Heat cure compound. This compound is an all round high performance compound, and is very similar to a Consil C molded or extruded elastomer. It has been traditionally used for telecommunications base station shielding. This material has excellent adhesive strength, and the electrical conductivity remains stable even under long term mechanical load such as vibration or periodic loading and temperature fluctuations. Information provided by Chomerics

Order this product through the following link:

http://www.lookpolymers.com/polymer_Parker-Chomerics-Tecknit-Teckfip-HC-FIP-C-Formed-in-Place-Conductive-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.23 - 2.99 g/cc	2.23 - 2.99 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45 - 55	45 - 55	
Tensile Strength	>= 1.38 MPa	>= 200 psi	
Elongation at Break	>= 50 %	>= 50 %	
Peel Strength	>= 9.00 kN/m	>= 51.4 pli	
Compression Set	10 - 25 %	10 - 25 %	
	27 %	27 %	
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-55.0 °C	-67.0 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	<= 0.010 ohm-cm	<= 0.010 ohm-cm	
Surface Resistance	<= 0.010 ohm	<= 0.010 ohm	
	<= 0.030 ohm	<= 0.030 ohm	
	@Temperature 85.0 °C, Time 605000 sec	@Temperature 185 °F, Time 168 hour	

Processing Properties	Metric	English	Comments
Cure Time	60.0 min	1.00 hour	
	@Temperature 125 °C	@Temperature 257 °F	
Shelf Life	1.00 Month	1.00 Month	Syringe
	6.00 Month	6.00 Month	Cartridge

Descriptive Properties	Value	Comments
Color	Gray	
Filler	Silver/Copper Heat Cure	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China