

Permabond HH040 Pure NSF 61 Approved Anaerobic Retainer

Category : Polymer , Adhesive , Thermoset

Material Notes:

Permabond® HH040 PURE is a single component liquid that cures only when in contact with metal parts and oxygen is excluded. The liquid adhesive fills the "air space" between parts and upon cure unitizes and retains male and female parts. Thus it prevents their movement relative to each other, eliminating wear, erosion, and pitting. HH040 PURE cures to a tough cross-linked plastic that will prevent the corrosion of mated parts, and provides excellent environmental and temperature resistance. PERMABOND® HH040 PURE Anaerobic Retaining Compound conforms to all applicable requirements of the NSF/ANSI Standard 61, Drinking Water System Components - Health Effects, as certified by NSF International and the American National Standards Institute. Standard 61 establishes minimum health effects requirements for materials, components, products, or systems that contact drinking water or drinking water treatment chemicals. NSF standards are widely recognized by public health officials, and certified products have been tested and determined to cause no adverse health effects. This allows manufacturers using certified materials to bypass some or all chemical testing when seeking NSF certification.

Features & Benefits: NSF certified drinking water system component Simple one-part system Shaft-hub assemblies can be made with slip fits Expensive press fits can be eliminated High viscosity for maximum gap filling ability Excellent shear strength Superior environmental resistance Thixotropic viscosity allows easy dispensing Information provided by Permabond.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Permabond-HH040-Pure-NSF-61-Approved-Anaerobic-Retainer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	Uncured
Viscosity	5000 cP @Temperature 25.0 °C	5000 cP @Temperature 77.0 °F	Uncured
Storage Temperature	5.00 - 25.0 °C	41.0 - 77.0 °F	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	14.0 MPa	2030 psi	steel collar and pin shear; ISO 10123

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 µm/m-°C	50.0 µin/in-°F	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft²-°F	
Maximum Service Temperature, Air	149 °C	300 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	11.0 kV/mm	279 kV/in	

Processing Properties	Metric	English	Comments
Cure Time	4.98 min	0.0830 hour	Brass, handling strength
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	15.0 min	0.250 hour	M10 steel, handling strength
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	30.0 min	0.500 hour	Brass, working strength
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	60.0 min	1.00 hour	Zinc, handling strength
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	60.0 min	1.00 hour	M10 steel, working strength
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	360 min	6.00 hour	Stainless steel, handling strength
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	360 - 1440 min	6.00 - 24.0 hour	Zinc, working strength
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	1440 min	24.0 hour	M10 steel, full strength
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Descriptive Properties	Value	Comments
Appearance	Colorless to Light Amber	Uncured
Maximum Gap Fill (mm)	0.25	
Maximum Thread Size	M30	
Strength Retention	50% at 150°C	Relative to 0°C
	80% at 100°C	Relative to 0°C
	93% at 50°C	Relative to 0°C
Torque Strength (N m)	25	M10 steel, break
	37	M10 steel, prevail

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China