

Phillips 66 COPYLENE® CR350CL Polypropylene, Random Copolymer, Clarified, Lubricated

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

COPYLENE™ CR350CL is a clarified, easy molding high melt flow polypropylene random copolymer resin with good see-through and contact clarity in injection molding applications. Applications: Housewares, Clear containers Information provided by Phillips 66.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Phillips-66-COPYLENE-CR350CL-Polypropylene-Random-Copolymer-Clarified-Lubricated.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in³	ASTM D792
Melt Flow	35 g/10 min	35 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.3 MPa	4100 psi	2 in/min; ASTM D638
Elongation at Yield	12 %	12 %	ASTM D638
Flexural Modulus	1.10 GPa	160 ksi	0.05 in/min; 1% secant; Procedure A; ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	Method A; ASTM D256
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	82.0 °C	180 °F	unannealed; ASTM D648

Descriptive Properties	Value	Comments
Process	Injection Molding	
Region	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China