

Plaskolite Optix® CA-61 General Purpose Acrylic Resin

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

Material Notes:

Injection Molding and Extrusion Grade Pellets. Good heat resistance, medium flow.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plaskolite-Optix-CA-61-General-Purpose-Acrylic-Resin.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in³	ASTM D792
Melt Flow	6.0 g/10 min	6.0 g/10 min	Condition 230/2-8; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	66.0 MPa	9570 psi	ASTM D638
Elongation at Break	3.4 %	3.4 %	ASTM D638
Modulus of Elasticity	3.00 GPa	435 ksi	ASTM D638
Flexural Strength	108 MPa	15700 psi	ASTM D790
Izod Impact, Notched	0.160 J/cm	0.300 ft-lb/in	ASTM D256
Gardner Impact	0.226 J	0.167 ft-lb	Falling Weight; ASTM D3029GB

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	91.0 °C	196 °F	ASTM D648
Vicat Softening Point	102 °C	216 °F	ASTM D1525
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Transmission, Visible	92 %	92 %	Luminous Transmittance, ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China