

Plaskolite Optix® PL-76 Acrylic Resin (discontinued **)

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, Optical Grade, Molded

Material Notes:

Injection/extrusion pellets. Medium heat resistance with higher flow than PL-52 pellets. Data provided by the manufacturer, Plaskolite, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plaskolite-Optix-PL-76-Acrylic-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ASTM D792
Water Absorption	0.30 %	0.30 %	ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	48 hrs; ASTM D955
Melt Flow	7.5 g/10 min	7.5 g/10 min	Condition I; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	94	94	Method A; ASTM D785
Tensile Strength, Yield	72.0 MPa	10400 psi	ASTM D638
Tensile Modulus	3.00 GPa	435 ksi	ASTM D638
Flexural Yield Strength	110 MPa	16000 psi	ASTM D790
Izod Impact, Notched	0.400 J/cm	0.749 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	72.0 µm/m-°C	40.0 µin/in-°F	ASTM D696
	@Temperature -18.0 - 38.0 °C	@Temperature -0.400 - 100 °F	
Specific Heat Capacity	1.50 J/g-°C	0.359 BTU/lb-°F	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ASTM C177
Melting Point	152 °C	306 °F	Flow temperature; ASTM D569
Deflection Temperature at 1.8 MPa (264 psi)	93.0 °C	199 °F	ASTM D648
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	n _D ; ASTM D542

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.7	3.7	ASTM D150
	@Frequency 60 Hz	@Frequency 60 Hz	
Dielectric Strength	18.0 kV/mm	457 kV/in	ASTM D149
Dissipation Factor	0.050	0.050	ASTM D150
	@Frequency 60 Hz	@Frequency 60 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China