

Plastcom SLOVALEN PH 91 N Polypropylene Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Features Modified homopolymer PP for injection moulding. General use in all industry branches - packing material, garden flower-pots, toys, furniture industry, hinges, fasteners, clamps, office chairs, hangers etc. Delivered in natural and in the full RAL color scale. Application: Injection Moulding Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVALEN-PH-91-N-Polypropylene-Homopolymer.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	STN 64 0111
Linear Mold Shrinkage	0.018 cm/cm	0.018 in/in	STN 64 0808
Linear Mold Shrinkage, Transverse	0.0193 cm/cm	0.0193 in/in	STN 64 0808
Melt Flow	25 g/10 min @Load 2.16 kg, Temperature 230 °C	25 g/10 min @Load 4.76 lb, Temperature 446 °F	STN EN ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	30.0 MPa	4350 psi	STN EN ISO 527-2
Elongation at Break	150 %	150 %	STN EN ISO 527-2
Tensile Modulus	1.50 GPa	218 ksi	STN EN ISO 527-2
Flexural Strength	40.0 MPa	5800 psi	STN EN ISO 178
Flexural Modulus	1.10 GPa	160 ksi	STN EN ISO 178
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	STN EN ISO 179
Charpy Impact, Notched	0.500 J/cm ² @Temperature 23.0 °C	2.38 ft-lb/in ² @Temperature 73.4 °F	STN EN ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	160 °C	320 °F	DSC; STN EN ISO 3146
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	STN EN ISO 75/A
Vicat Softening Point	150 °C	302 °F	B; STN EN ISO 306

Processing Properties	Metric	English	Comments
Melt Temperature	200 - 250 °C	392 - 482 °F	
Mold Temperature	30.0 - 50.0 °C	86.0 - 122 °F	
Injection Pressure	60.0 - 70.0 MPa	8700 - 10200 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China