

Plastcom SLOVAMID 66 GF 25 FRI 3 TS PA66, 25% glass fibre, flame retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Glass Fiber Filled, Flame Retardant

Material Notes:

FeaturesPA 66 for injection moulding, chemically reinforced with 25% glass fibre and non-halogen flame retardant, with heat resistance and nonflammability, achieves V 0 in accordance with UL 94. Nonhalogen flame retardant on the basis of red phosphorus guarantees excellent electric parameters like eg. electric strength and CTI. Application in electrotechnical industry: breakers, coil forms, covers, terminals. Delivered in natural and black mode.Packaging, transport, stockingThe product is packed in hermetically closed thick-walled 25 kg PE bags, on a 1.000 kg palette coated in a stretch foil, in big bags with a thick PE foil fixed on a 1.000 kg palette, in paper octabins with a thick PE foil fixed on a 1.000 kg palette or in other packaging according to customer requirements. The transport is provided in closed-up vehicles where the material is protected against movement and mechanical damage. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVAMID-66-GF-25-FRI-3-TS-PA66-25-glass-fibre-flame-retardant.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	
Viscosity Measurement	0.52 - 0.97	0.52 - 0.97	
Linear Mold Shrinkage	0.0052 cm/cm	0.0052 in/in	
Linear Mold Shrinkage, Transverse	0.0097 cm/cm	0.0097 in/in	
Melt Flow	1.0 g/10 min @Load 0.325 kg, Temperature 270 °C	1.0 g/10 min @Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	135 MPa	19600 psi	
Elongation at Break	3.0 %	3.0 %	
Tensile Modulus	6.50 GPa	943 ksi	
Flexural Strength	190 MPa	27600 psi	
Flexural Modulus	5.70 GPa	827 ksi	
Charpy Impact Unnotched	4.50 J/cm ² @Temperature -20.0 °C	21.4 ft-lb/in ² @Temperature -4.00 °F	
	5.00 J/cm ² @Temperature 23.0 °C	23.8 ft-lb/in ² @Temperature 73.4 °F	

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	0.700 J/cm²	3.33 ft-lb/in²	
	@Temperature -20.0 °C	@Temperature -4.00 °F	
	0.800 J/cm²	3.81 ft-lb/in²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	
Vicat Softening Point	250 °C	482 °F	B
Flammability, UL94	V-0	V-0	
Glow Wire Test	960 °C	1760 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	
Dielectric Strength	70.0 kV/mm	1780 kV/in	
Comparative Tracking Index	550 V	550 V	

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 300 °C	536 - 572 °F	
Mold Temperature	70.0 - 90.0 °C	158 - 194 °F	
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.15 %	0.15 %	
Injection Pressure	70.0 - 120 MPa	10200 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China