

Plastcom SLOVASTER® B2 BT PBT, basic type

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

FeaturesPBT basic type for injection molding. Melt is characterised by outstanding fluidity, which enables injection molding of complicated and divided products also on multiple molds. Anisotropy of shrinkage enables injection moulding of round, cylindric or other hole products. Delivered in natural color and in the full RAL color scale.Packaging, transport, stocking. The product requires stocking in closed-up, dry places protected against sun and thermal radiation.Information Provided by Plastcom spol. s r.o.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastcom-SLOVASTER-B2-BT-PBT-basic-type.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in³	
Linear Mold Shrinkage	0.018 cm/cm	0.018 in/in	
Linear Mold Shrinkage, Transverse	0.0193 cm/cm	0.0193 in/in	
Melt Flow	20 g/10 min @Load 0.325 kg, Temperature 270 °C	20 g/10 min @Load 0.716 lb, Temperature 518 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	
Elongation at Break	4.0 %	4.0 %	
Tensile Modulus	2.50 GPa	363 ksi	
Flexural Strength	80.0 MPa	11600 psi	
Flexural Modulus	2.50 GPa	363 ksi	
Charpy Impact Unnotched	NB @Temperature -20.0 °C	NB @Temperature -4.00 °F	
	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	
Charpy Impact, Notched	0.400 J/cm² @Temperature -20.0 °C	1.90 ft-lb/in² @Temperature -4.00 °F	
	0.600 J/cm² @Temperature 23.0 °C	2.86 ft-lb/in² @Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	200 - 220 °C	392 - 428 °F	
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	
Vicat Softening Point	200 °C	392 °F	B
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	
Comparative Tracking Index	550 V	550 V	

Processing Properties	Metric	English	Comments
Melt Temperature	250 - 270 °C	482 - 518 °F	
Mold Temperature	50.0 - 80.0 °C	122 - 176 °F	
Drying Temperature	120 °C	248 °F	
Dry Time	4 hour	4 hour	
Moisture Content	0.050 %	0.050 %	
Injection Pressure	60.0 - 100 MPa	8700 - 14500 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China