

PlastiComp Complet® LGF40 - PA6 Nylon 6, 40% Long Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 40% Glass Fiber Filled

Material Notes:

Complēt® long-fiber reinforced pellets are manufactured to exceed expectation for quality and performance. Nylon 6 with 40% long glass fiber reinforcement. Information provided by PlastiComp, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastiComp-Complet-LGF40-PA6-Nylon-6-40-Long-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D-792
Filler Content	40 %	40 %	Long Glass Fiber

Mechanical Properties	Metric	English	Comments
Tensile Strength	235 MPa	34100 psi	ASTM D-638
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	ASTM D-638
Tensile Modulus	12.931 GPa	1875.5 ksi	ASTM D-638
Flexural Strength	316 MPa	45800 psi	ASTM D-790
Flexural Modulus	12.069 GPa	1750.5 ksi	ASTM D-790
Izod Impact, Notched	2.67 J/cm	5.00 ft-lb/in	ASTM D-256
Izod Impact, Unnotched	13.88 J/cm	26.00 ft-lb/in	ASTM D-4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	213 °C	415 °F	ASTM D-648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	260 - 277 °C	500 - 530 °F	
Middle Barrel Temperature	266 - 282 °C	510 - 540 °F	
Front Barrel Temperature	271 - 288 °C	520 - 550 °F	
Nozzle Temperature	271 - 288 °C	520 - 550 °F	
Melt Temperature	271 - 288 °C	520 - 550 °F	
Mold Temperature	93.3 °C	200 °F	
Injection Velocity			

Processing Properties	50.8 - 76.2 mm/sec Metric	2.00 - 3.00 in/sec English	Comments
Drying Temperature	85.0 °C	185 °F	
	@Time 14400 sec	@Time 4.00 hour	
Moisture Content	<= 0.18 %	<= 0.18 %	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Cushion	0.635 cm	0.250 in	
Screw Speed	30 - 50 rpm	30 - 50 rpm	

Descriptive Properties	Value	Comments
Injection Pressure	Medium to maximum	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China