

PlastiComp Complet® LGF50 - TPU Rigid Thermoplastic Polyurethane, 50% Long Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Glass Fiber Reinforced

Material Notes:

Complēt® long-fiber reinforced pellets are manufactured to exceed expectation for quality and performance. Rigid polyurethane with 50% long glass fiber reinforcement. Information provided by PlastiComp, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastiComp-Complet-LGF50-TPU-Rigid-Thermoplastic-Polyurethane-50-Long-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	ASTM D-792
Filler Content	50 %	50 %	Long Glass Fiber

Mechanical Properties	Metric	English	Comments
Tensile Strength	221 MPa	32100 psi	ASTM D-638
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	ASTM D-638
Tensile Modulus	15.172 GPa	2200.5 ksi	ASTM D-638
Flexural Strength	359 MPa	52100 psi	ASTM D-790
Flexural Modulus	15.172 GPa	2200.5 ksi	ASTM D-790
Izod Impact, Notched	6.41 J/cm	12.0 ft-lb/in	ASTM D-256
Izod Impact, Unnotched	16.02 J/cm	30.01 ft-lb/in	ASTM D-4812

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	114 °C	237 °F	ASTM D-648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	204 - 227 °C	400 - 440 °F	
Middle Barrel Temperature	210 - 232 °C	410 - 450 °F	
Front Barrel Temperature	216 - 238 °C	420 - 460 °F	
Nozzle Temperature	221 - 243 °C	430 - 470 °F	
Melt Temperature	216 - 238 °C	420 - 460 °F	

Mold Temperature Processing Properties	87.8 °C Metric	190 °F English	Comments
Injection Velocity	50.8 - 76.2 mm/sec	2.00 - 3.00 in/sec	
Drying Temperature	88.0 °C @Time 14400 sec	190 °F @Time 4.00 hour	
Moisture Content	<= 0.020 %	<= 0.020 %	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Cushion	0.635 cm	0.250 in	
Screw Speed	30 - 50 rpm	30 - 50 rpm	

Descriptive Properties	Value	Comments
Injection Pressure	Medium to maximum	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China