

Plastics Group Polifil® T-10 10% Talc-Reinforced Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Polifil® T series compounds are homopolymer polypropylene resins reinforced with asbestos-free talc. They possess high flex modulus, high deflection temperature, good chemical resistance and colorability, low shrinkage and yield maximum stiffness combined with characteristic impact. Applications: Automotive (underhood) applications Major appliances Electrical goods Housewares Standard processing techniques are applicable. Information provided by The Plastics Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plastics-Group-Polifil-T-10-10-Talc-Reinforced-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.980 g/cc	0.0354 lb/in ³	ASTM D792
Filler Content	10 %	10 %	ASTM D2584
Linear Mold Shrinkage	0.012 cm/cm @Thickness 1.59 mm	0.012 in/in @Thickness 0.0625 in	ASTM D955
Melt Flow	8.0 - 12 g/10 min	8.0 - 12 g/10 min	230/2.16; May be specified; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	97	97	ASTM D785
Tensile Strength at Break	28.3 MPa	4100 psi	ASTM D638
Flexural Modulus	1.86 GPa	270 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.400 J/cm	0.750 ft-lb/in	At 73°F; ASTM D256
Izod Impact, Unnotched	3.58 J/cm	6.70 ft-lb/in	At 73°F; ASTM D256
Gardner Impact	0.565 J	0.417 ft-lb	ASTM D3029

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	118 °C	245 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China