

PlastxWorld CEVIAN® A2606 30% GF PA/ABS Alloy, DAM

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS)/Nylon Blend, Glass Reinforced , Nylon

Material Notes:

Property data is for dry as molded (DAM) samples. These are typical values and are not intended for specification purposes. UL approved file No. is E47773. Information provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-CEVIAN-A2606-30-GF-PAABS-Alloy-DAM.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	ASTM D792
Water Absorption	0.70 %	0.70 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0010 - 0.0050 cm/cm	0.0010 - 0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	ASTM D785
Tensile Strength at Break	124 MPa	18000 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D635
Flexural Yield Strength	179 MPa	26000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	195 °C	383 °F	0.5 inch; ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China