

PlastxWorld DAICEL STYROL® SK60 HIPS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Flame Retardant

Material Notes:

UV stable flame retarded HIPSThese are typical values and are not intended for specification purposes. UL approved file No. is E47773.

Information provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-DAICEL-STYROL-SK60-HIPS.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	ASTM D792
Water Absorption	0.10 %	0.10 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D955
Melt Flow	4.0 g/10 min @Load 5.00 kg, Temperature 200 °C	4.0 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	94	94	ASTM D785
Tensile Strength at Break	30.3 MPa	4400 psi	ASTM D638
Flexural Yield Strength	49.0 MPa	7110 psi	ASTM D790
Flexural Modulus	2.45 GPa	355 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	80.0 °C	176 °F	0.25 inch; ASTM D648
Vicat Softening Point	94.0 °C	201 °F	ASTM D1525
Flammability, UL94	V-2 @Thickness 1.30 mm	V-2 @Thickness 0.0512 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China