

PlastxWorld Veroplas PA2002 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

general purpose, unfilled, impact modified injection molding grade Information provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-Veroplas-PA2002-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM A792
Moisture Absorption at Equilibrium	<= 0.17 %	<= 0.17 %	Karl Fischer
Linear Mold Shrinkage	0.024 cm/cm	0.024 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	60.0 MPa	8700 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Flexural Yield Strength	70.3 MPa	10200 psi	ASTM D790
Flexural Modulus	2.10 GPa	305 ksi	ASTM D790
Izod Impact, Notched	1.20 J/cm	2.25 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	49.0 °C	120 °F	ASTM D648
Vicat Softening Point	171 °C	340 °F	ASTM D1525
Glow Wire Test	649 °C	1200 °F	UNE 20-672-83

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China