

PlastxWorld Veroplas PB2001F Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Unreinforced, Flame Retardant

Material Notes:

flame retarded (UL94 V0), unfilled injection molding grade Information provided by PlastxWorld Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PlastxWorld-Veroplas-PB2001F-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM A792
Moisture Absorption at Equilibrium	<= 0.17 %	<= 0.17 %	Karl Fischer
Linear Mold Shrinkage	0.020 cm/cm	0.020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	80.0 MPa	11600 psi	ASTM D638
Elongation at Break	15 %	15 %	ASTM D638
Flexural Yield Strength	100 MPa	14500 psi	ASTM D790
Flexural Modulus	3.00 GPa	435 ksi	ASTM D790
Izod Impact, Notched	0.448 J/cm	0.840 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	99.0 °C	210 °F	ASTM D648
Vicat Softening Point	199 °C	390 °F	ASTM D1525
Flammability, UL94	V-0 @Thickness 2.50 mm	V-0 @Thickness 0.0984 in	
Glow Wire Test	960 °C	1760 °F	UNE 20-672-83

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China