

Plenco 50130 PET, Pellet, Injection Molded, Black (discontinued **)

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET)

Material Notes:

PLENCO 50130 is an engineering grade glass reinforced UL flame rated polyethylene terephthalate resin designed for good physical strength. It is UL listed and available in natural and black. Information supplied by Plenco. Plenco discontinued their PET product line in 2005.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Plenco-50130-PET-Pellet-Injection-Molded-Black-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.73 g/cc	0.0625 lb/in ³	ASTM D792
Water Absorption	0.050 %	0.050 %	ASTM D570
Linear Mold Shrinkage	0.00090 cm/cm	0.00090 in/in	ATM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	137.9 MPa	20000 psi	ASTM D638
Elongation at Break	1.65 %	1.65 %	ASTM D638
Tensile Modulus	11.41 GPa	1655 ksi	ASTM D638
Flexural Yield Strength	206.1 MPa	29890 psi	ASTM D790
Flexural Modulus	10.94 GPa	1587 ksi	ASTM D790
Compressive Yield Strength	164.7 MPa	23890 psi	ASTM D695
Izod Impact, Notched	0.680 J/cm	1.27 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	220 °C	428 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 1.47 mm	V-0 @Thickness 0.0579 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	5.9566e+17 ohm-cm	5.9566e+17 ohm-cm	ASTM D257
Dielectric Constant	3.4 @Frequency 1e+6 Hz	3.4 @Frequency 1e+6 Hz	ASTM D150

Dielectric Strength Electrical Properties	16.1 kV/mm Metric	409 kV/in English	Short Time: ASTM D149 Comments
Dissipation Factor	0.011 @Frequency 1e+6 Hz	0.011 @Frequency 1e+6 Hz	ASTM D150
Arc Resistance	40 sec	40 sec	ASTM D495
Comparative Tracking Index	200 V	200 V	ASTM D3638

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China