

Polimeri Europa EDISTIR N1671 Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS)

Material Notes:

Symbol according to ISO 1043-1: PS Designation: Thermoplastic ISO 1622-PS,M,095-06 General purpose polystyrene with good flow and good heat resistance for rapid set-up. To be used in injection molding of items with complex and medium thick walls. Applications: Typical uses are domestic appliances, stationery, cutlery, housewares and medical articles. Unfilled. Suitable for Injection Molding. Supplied as pellets. Contains release agent. ISO data. Information provided by Enichem Polimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-EDISTIR-N1671-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	
Melt Flow	5.4 g/10 min @Load 5.00 kg, Temperature 200 °C	5.4 g/10 min @Load 11.0 lb, Temperature 392 °F	cm ³ /10 min

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	42.0 MPa	6090 psi	5 mm/min
Elongation at Break	2.0 %	2.0 %	5 mm/min
Tensile Modulus	3.28 GPa	476 ksi	1 mm/min
Charpy Impact Unnotched	1.00 J/cm ²	4.76 ft-lb/in ²	
Charpy Impact, Notched	0.200 J/cm ²	0.952 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	82.0 °C	180 °F	
Vicat Softening Point	94.0 °C	201 °F	50°C/hr; 50N
Glass Transition Temp, Tg	95.0 °C	203 °F	10°C/min test
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Optical Properties	Metric	English	Comments
Transmission, Visible	80 %	80 %	Manufacturer specifies 'transparent' but doesn't quantify.

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00\text{e}+15$ ohm-cm	$\geq 1.00\text{e}+15$ ohm-cm	
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	
Dielectric Constant	2.5	2.5	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	70.0 kV/mm	1780 kV/in	
Dissipation Factor	0.00020	0.00020	
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	400 V	400 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China