

Polimeri Europa Riblene® FL 24 Low Density Polyethylene - Blown Film Extrusion

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

Material Notes:

Riblene FL 24 is a low density polyethylene (LDPE) with added slip and antiblocking agents, suitable for blown film extrusion. Riblene FL 24 is characterized by a good balance between processability and mechanical properties. Films manufactured with Riblene FL 24 are easily heat shrinkable and have good optical properties. Main Applications: Riblene FL 24 is recommended for general packaging film, for the production of thin and shrink film and for blend. Information provided by Polimeri Europa.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-Riblene-FL-24-Low-Density-Polyethylene-Blown-Film-Extrusion.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.921 g/cc	0.921 g/cc	ISO 1183
Thickness	25.0 - 80.0 microns	0.984 - 3.15 mil	Recommended
Melt Flow	2.2 g/10 min @Load 2.16 kg, Temperature 190 °C	2.2 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	11.0 MPa	1600 psi	ISO 527-3
Film Tensile Strength at Yield, TD	10.0 MPa	1450 psi	ISO 527-3
Film Elongation at Break, MD	300 %	300 %	ISO 527-3
Film Elongation at Break, TD	600 %	600 %	ISO 527-3
Coefficient of Friction, Dynamic	0.11	0.11	ISO 8295
Elmendorf Tear Strength, MD	7.133 g/micron	181.2 g/mil	ISO 6383-2
Elmendorf Tear Strength, TD	4.5855 g/micron	116.47 g/mil	ISO 6383-2
Dart Drop Test	195 g	0.430 lb	F50; ISO 7765-1
Film Tensile Strength at Break, MD	25.0 MPa	3630 psi	ISO 527-3
Film Tensile Strength at Break, TD	23.0 MPa	3340 psi	ISO 527-3
1% Secant Modulus, MD	170 MPa	24700 psi	ISO 527-3
1% Secant Modulus, TD	180 MPa	26100 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Vicat Softening Point	90.0 °C	194 °F	ISO 306/A
	@Load 1.00 kg	@Load 2.20 lb	
Brittleness Temperature	<= -75.0 °C	<= -103 °F	ASTM D746

Optical Properties	Metric	English	Comments
Haze	10 %	10 %	ISO 14782
Gloss	60 %	60 %	45°; ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China