

## Polimeri Europa SINKRAL C333/m<sup>2</sup> ABS, Heat Stabilized (discontinued \*\*)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Heat Resistant, Molded

### Material Notes:

Symbol according to ISO 1043-1: ABS Grade designation according to ISO 2580-ABS 1, MG, 105-04-16-20 Special low gloss grade for injection moulding which combines medium heat resistance with a good balance between stiffness & toughness. The main field of application for this grade is automotive interiors, for example dashboard instruments and panels, where a matt surface finish and thermal resistance are highly desirable. The choice of this material, when properly processed in tools having a suitable quality finish, can mean the elimination of subsequent painting operations with a consequent reduction in part costs, together with easier recycling. Unfilled. Suitable for Injection Molding. Supplied as pellets. Contains lubricant and release agent. ISO data. Information provided by Enichem Polimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Polimeri-Europa-SINKRAL-C333m-ABS-Heat-Stabilized-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Polimeri-Europa-SINKRAL-C333m-ABS-Heat-Stabilized-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in <sup>3</sup>	
Water Absorption	1.0 %	1.0 %	
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Humidity Absorption
Melt Flow	5.0 g/10 min @Load 10.0 kg, Temperature 220 °C	5.0 g/10 min @Load 22.0 lb, Temperature 428 °F	cm <sup>3</sup> /10 min

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	33.0 MPa	4790 psi	50 mm/min
Elongation at Break	>= 50 %	>= 50 %	Nominal
Elongation at Yield	3.0 %	3.0 %	50 mm/min
Tensile Modulus	1.90 GPa	276 ksi	1 mm/min
Charpy Impact Unnotched	NB	NB	
	15.0 J/cm <sup>2</sup> @Temperature -30.0 °C	71.4 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	
Charpy Impact, Notched	1.50 J/cm <sup>2</sup>	7.14 ft-lb/in <sup>2</sup>	
	0.800 J/cm <sup>2</sup> @Temperature -30.0 °C	3.81 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	n/m-°C	in/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	96.0 °C	205 °F	
Deflection Temperature at 1.8 MPa (264 psi)	83.0 °C	181 °F	
Vicat Softening Point	101 °C	214 °F	50°C/hr; 50N
Glass Transition Temp, Tg	109 °C	228 °F	10°C/min test
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Comparative Tracking Index	600 V	600 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China