

Polimeri Europa SINKRAL G323 ABS (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Symbol according to ISO 1043-1: ABS Grade designation according to ISO 2580-ABS 1,MG,095-15-16-20 General purpose injection moulding grade. Main properties are: good impact resistance high flow excellent processing stability Ideally suited for compounding to produce coloured ABS.Unfilled. Suitable for Injection Molding. Supplied as pellets. Contains lubricant and release agent.ISO data. Information provided by EnichemPolimeri Europa now has Enichem's plastics businesses. This grade is no longer in the product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Polimeri-Europa-SINKRAL-G323-ABS-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	
Water Absorption	1.0 %	1.0 %	
Moisture Absorption at Equilibrium	0.20 %	0.20 %	Humidity Absorption
Melt Flow	20 g/10 min @Load 10.0 kg, Temperature 220 °C	20 g/10 min @Load 22.0 lb, Temperature 428 °F	cm ³ /10 min

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	45.0 MPa	6530 psi	50 mm/min
Elongation at Break	20 %	20 %	Nominal
Elongation at Yield	3.0 %	3.0 %	50 mm/min
Tensile Modulus	2.25 GPa	326 ksi	1 mm/min
Charpy Impact Unnotched	16.0 J/cm ²	76.1 ft-lb/in ²	
	10.0 J/cm ² @Temperature -30.0 °C	47.6 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	1.70 J/cm ²	8.09 ft-lb/in ²	
	0.800 J/cm ² @Temperature -30.0 °C	3.81 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 µm/m-°C @Temperature 20.0 °C	50.0 µin/in-°F @Temperature 68.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (264 psi)	82.0 °C	180 °F	
Vicat Softening Point	97.0 °C	207 °F	50°C/hr; 50N
Glass Transition Temp, Tg	108 °C	226 °F	10°C/min test
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Strength	30.0 kV/mm	762 kV/in	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China