

PolyMirae Moplen HF524J BDDP Film Grade Polypropylene

Category : Polymer , Film , Thermoplastic , Polypropylene (PP) , Polypropylene, Film Grade

Material Notes:

Moplen HF524J is the Addiform polypropylene. Compared to ordinary pelletized polypropylene, Addiform gives significant advantages in terms of improved productivity, better processing and lower energy consumption. End products have also been found to have superior characteristics when using Addiform in a number of application areas. Moplen HF524J is the homopolymer manufactured by PMC under the license of BASSELL using the Spheripol process. MIRAEPOL PA124VS is a homopolymer particularly suitable for BOPP (Tender). Moplen HF524J resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 178.2010 for food packaging substances with adequate additives. And contains no dangerous substances according to Federal Regulations in 21 CFR 177.1520. Features: High Transparency and Gloss; Excellent processability; High stiffness and strength; Good barrier property; Increasing output and low energy consumption Applications: General purpose packaging; Lamination Film; Adhesive tape Information provided by PolyMirae Company Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyMirae-Moplen-HF524J-BDDP-Film-Grade-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	0.900 g/cc	0.0325 lb/in ³	ASTM D1505
Melt Flow	3.0 g/10 min @Load 2.16 kg, Temperature 230 °C	3.0 g/10 min @Load 4.76 lb, Temperature 446 °F	Condition L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	98	98	ASTM D785
Tensile Strength, Yield	36.3 MPa	5260 psi	ASTM D638
Elongation at Yield	12 %	12 %	ASTM D638
Flexural Modulus	1.57 GPa	228 ksi	ASTM D790
Izod Impact, Notched	0.490 J/cm	0.918 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	105 °C	221 °F	ASTM D648
Vicat Softening Point	153 °C	307 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China