

**PolyOne Edgetek® AT-30GF/000 FDA Acetal-Copolymer, Glass Filled
(discontinued **)**

Category : Polymer , Thermoplastic , Acetal (POM)

Material Notes:
Description/Features:Glass Fiber ReinforcedFDA CapablePolyOne First ChoiceInformation provided by PolyOne Corporation.

Order this product through the following link:
http://www.lookpolymers.com/polymer_PolyOne-Edgetek-AT-30GF000-FDA-Acetal-Copolymer-Glass-Filled-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.62 g/cc	1.62 g/cc	ASTM D792
Water Absorption	0.0080 %	0.0080 %	24 hr. Immersion; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0035 cm/cm	0.0030 - 0.0035 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	75.8 MPa	11000 psi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Elongation at Break	3.0 %	3.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	6.89 GPa	1000 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	96.5 MPa	14000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 6.35 mm, Temperature 23.0 °C	1.50 ft-lb/in @Thickness 0.250 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	210 - 238 °C	410 - 460 °F	Molding
Mold Temperature	54.4 - 71.1 °C	130 - 160 °F	
Drying Temperature	71.1 °C	160 °F	
Dry Time	2 hour	2 hour	

Descriptive Properties	Value	Comments
Product Form	Pellets	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China