

PolyOne Edgetek® SF-30GF/000 Polyphenylene Sulfide (PPS), Glass Filled (discontinued **)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

Description/Features: Glass Fiber Reinforced UL 94 V0 PolyOne First Choice Information provided by PolyOne Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-SF-30GF000-Polyphenylene-Sulfide-PPS-Glass-Filled-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.56 g/cc	1.56 g/cc	ASTM D792
Water Absorption	0.040 % @Thickness 3.17 mm	0.040 % @Thickness 0.125 in	24 hr immersion; ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0030 cm/cm	0.0020 - 0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	138 MPa	20000 psi	Type 1 - Rigids, Yield, 0.2 in/min; ASTM D638
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	Type 1 - Rigids, 0.2 in/min; ASTM D638
Tensile Modulus	13.1 GPa	1900 ksi	Type 1 - Rigids, 0.2 in/min; ASTM D638
Flexural Strength	200 MPa	29000 psi	ASTM D790
Flexural Modulus	13.1 GPa	1900 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 3.17 mm, Temperature 23.0 °C	1.50 ft-lb/in @Thickness 0.125 in, Temperature 73.4 °F	Method A, Injection Molded; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	260 °C	500 °F	Unannealed; ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	316 - 327 °C	600 - 620 °F	Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China