

PolyOne Edgetek® XT XT-115GF-AX01-HF PC+PBT with Glass Fiber Reinforcement (discontinued **)

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Glass Filled , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

EDGE TEK™ XT High Performance Polymers are polycarbonate and polyester alloys that combine strength, durability and chemical resistance. The Edgetek XT product family includes a complete line of general purpose, UV stable and low -temperature impact grades for use in a wide range of demanding applications and severe operating environments plus customized formulations to meet specialized requirements.

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Edgetek-XT-XT-115GF-AX01-HF-PCPBT-with-Glass-Fiber-Reinforcement-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.30 g/cc	1.30 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	85.5 MPa	12400 psi	Type I, 5.1 mm/min; ASTM D638
Elongation at Break	4.5 %	4.5 %	Type I, 5.1 mm/min; ASTM D638
Flexural Strength	134 MPa	19400 psi	ASTM D790
Flexural Modulus	4.55 GPa	660 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	Injection Molded; ASTM D256A
	@Thickness 3.18 mm, Temperature -20.0 °C	@Thickness 0.125 in, Temperature -4.00 °F	
	1.44 J/cm	2.70 ft-lb/in	Injection Molded; ASTM D256A
	@Thickness 3.18 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	113 °C	235 °F	Annealed; ASTM D648
	@Thickness 6.35 mm	@Thickness 0.250 in	

Processing Properties	Metric	English	Comments
Melt Temperature	260 - 282 °C	500 - 540 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	

Processing Properties	Metric	English	Comments
Drying Temperature	@Time 7200 sec	@Time 2.00 hour	

Descriptive Properties	Value	Comments
Features	High Flow	
Forms	Pellets	
Generic Name	Polycarbonate + PBT (PC+PBT)	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China