

PolyOne Geon™ 130 Series 136 Polyvinyl Chloride Copolymer (PVC Copolymer)

Category: Polymer, Thermoplastic, Vinyl (PVC)

Material Notes:

Geon® 136 is a vinyl ester copolymer dispersion resin, exhibiting fast fusion at low processing temperatures, resulting in energy saving and the ability to work with heat sensitive substrates. The vinyl ester copolymers exhibit stable Brookfield Viscosity againg characteristics. The lower molecular weight resin, Geon® 136, allows lower processing (fusion) temperature compared to Geon® 138. It provides mechanically and chemically foamable. Geon® 136 is recommended for applications where low processing temperatures are required such as carpet tile and walk off mat backings, plastisol inks, general low temperature processing applications, automotive sealants.Note: The value set forth represent typical values and PolyOne Corporation, therefore, makes no representation that the material in any particular shipment will conform to the listed properties. Packaging: This resin is shipped in multi-wall paper bags, net weight 50 lbs, 2500 lbs per pallet.

Information shown on the package includes commercial identification number, lot and weight. Geon® ALTC and ASTM D638 (formulation): 100phr Geon® 136, 57phr DINP, 3phr ESO, and 2phr Therm-Chek SP 120 LOHF Geon® STP 390(formulation): 100phr Geon® 136, and 60phr D0PInformation provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-130-Series-136-Polyvinyl-Chloride-Copolymer-PVC-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Bulk Density	0.465 g/cc	0.0168 lb/in³	
Fineness	4.75	4.75	Hegman, North Fineness; Geon® 390
Relative Viscosity	2.37 cP	2.37 cP	Correlation, Cyclohexanone 1%; Internal Method
Brookfield Viscosity	4.33 cP	4.33 cP	Initial Viscosity @ 2 rpmGeon® ALTC 22 (with provided formulation); Internal Method
	4.6 cP	4.6 cP	Initial Viscosity @ 20 rpmGeon® ALTC 22 (with provided formulation); Internal Method
	5.55 cP	5.55 cP	One Day Viscosity @ 2 rpmGeon® ALTC 22 (with provided formulation); Internal Method
	6.18 cP	6.18 cP	One Day Viscosity @ 20 rpmGeon® ALTC 22 (with provided formulation); Internal Method
Viscosity Measurement	1.0	1.0	Inherent; ASTM D1243-60-A
Melt Flow	108 g/10 min	108 g/10 min	Severs Efflux; Geon® ALTC 23 (with provided formulation); Internal
	@Pressure 0.655 MPa	@Pressure 95.0 psi	Method

Mechanical Properties	Metric	English	Comments	

Karl FisherGeon® STP 683; Internal

Method



Moisture Content

Mechanical Properties	Metric Pa	English	Comments
Optical Properties	Metric	English	Comments
Gloss	93 %	93 %	60 Degree Fused 5 mins @ 350FGeon® ALTC 65 (with provided formulation); Internal Method
Transmission, Visible	93 %	93 %	Geon® ALTC 66 (with provided formulation); Internal Method
Processing Properties	Metric	English	Comments

0.050 %

0.050 %

Descriptive Properties	Value	Comments
Copolymer Content	4.9%	Internal Method; Geon® STP PT-LA-026
Features	Fast Fusion	
	Low VOC	
Forms	Powder	Fine, White Powder
Gel Temperature	65 °C	Internal Method; Geon® ALTC 29 (with provided formulation)
Generic Material	PVC Copolymer	
Generic Name	Polyvinyl Chloride Copolymer (PVC Copolymer)	
K-Value	70	Internal Method; Correlation, 0.5gm/100ml
Methanol Extractables	2.3%	Internal Method; Geon® STP 894
Polymerization Process	Microsuspension	
Processing Method	Casting	
	Dip Coating	
	Rotational Molding	
	Slush Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	

North America



Descriptive Properties	Value South America	Comments
Residual Vinyl Chloride Monomer	< 9 ppm	Internal Method; Geon® STP 1005
Uses	Automotive Applications	
	Carpet Backing	
	Sealants	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China