

PolyOne Geon™ Vinyl Flexible 90043 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Automotive OEM approval(s).Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-90043-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D792
Volatiles	0.30 % @Thickness 1.91 mm, Temperature 105 °C	0.30 % @Thickness 0.0752 in, Temperature 221 °F	Loss; Method A; ASTM D1203B

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	87	87	15 sec; ASTM D2240
Tensile Strength at Break	18.0 MPa	2610 psi	510 mm/min; ASTM D638
Elongation at Break	320 %	320 %	510 mm/min; ASTM D638
Tear Strength	62.3 kN/m	355 pli	Die C, 2 in/min; ASTM D1004

Descriptive Properties	Value	Comments
Automotive Specifications	CHRYSLER MS-DC211 Type B	
	CHRYSLER MS-DC211 Type B CPN2713 Color: 100% Color Match	
	GM GMP.PVC.010	
Features	High Gloss	
Forms	Pellets	
Fungal Resistance	Pass	ASTM G21
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Low Temperature Flexibility	Pass	-29°C, 508.0 µm; 4 hr, 12 mm
Processing Method	Extrusion	
Regional Availability	Africa & Middle East	

Descriptive Properties	Value	Comments
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Automotive Applications	
	Automotive Exterior Trim	
	Outdoor Applications	
Xenon Weatherometer	Pass	SAE J1960; Exterior, 301 kJ/m², All Colors, dE*<3.0

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China