

PolyOne Geon™ Vinyl Flexible A65M0 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Recommended for interior applications. Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-A65M0-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.023 - 0.027 cm/cm	0.023 - 0.027 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	15 sec; ASTM D2240
	65	65	ASTM D2240
Tensile Strength at Break	12.4 MPa	1800 psi	510 mm/min; ASTM D638
Tensile Strength	6.76 MPa	980 psi	510 mm/min; ASTM D638
	@Strain 100 %	@Strain 100 %	
Elongation at Break	340 %	340 %	510 mm/min; ASTM D638
Tear Strength	43.8 kN/m	250 pli	Die C, 510 mm/min; ASTM D624
Compression Set	45 %	45 %	ASTM D395
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-34.4 °C	-29.9 °F	ASTM D746

Optical Properties	Metric	English	Comments
Haze	3.0 %	3.0 %	ASTM D1003
	@Thickness 1.91 mm	@Thickness 0.0750 in	
Transmission, Visible	85 %	85 %	ASTM D1003
	@Thickness 1.91 mm	@Thickness 0.0750 in	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	Metric ^{179 °C}	English ^{34 °F}	Comments
	188 - 199 °C	370 - 390 °F	

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	
Features	High Gloss	
	Low to No Migration	
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China