

PolyOne Geon™ Vinyl Flexible B5D02 Polyvinyl Chloride, Flexible (PVC, Flexible)

Category : Polymer , Thermoplastic , Vinyl (PVC)

Material Notes:

Information provided by PolyOne

Order this product through the following link:

http://www.lookpolymers.com/polymer_PolyOne-Geon-Vinyl-Flexible-B5D02-Polyvinyl-Chloride-Flexible-PVC-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.29 g/cc	1.29 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0080 - 0.012 cm/cm	0.0080 - 0.012 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	36	36	15 sec; ASTM D2240
	50	50	ASTM D2240
Tensile Strength at Break	17.2 MPa	2490 psi	510 mm/min; ASTM D638
Tensile Strength	11.7 MPa	1700 psi	510 mm/min; ASTM D638
	@Strain 100 %	@Strain 100 %	
Elongation at Break	300 %	300 %	510 mm/min; ASTM D638
Tear Strength	84.1 kN/m	480 pli	Die C, 510 mm/min; ASTM D624
Compression Set	60 %	60 %	ASTM D395
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	
Clash Berg Modulus	0.565 GPa	81.9 ksi	ASTM D1043
	0.310 GPa	45.0 ksi	ASTM D1043
	@Temperature -28.0 °C	@Temperature -18.4 °F	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-23.9 °C	-11.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Melt Temperature	179 - 185 °C	354 - 365 °F	
	196 - 207 °C	385 - 405 °F	

Descriptive Properties	Value	Comments
Forms	Pellets	
Generic Material	PVC, Flexible	
Generic Name	Polyvinyl Chloride, Flexible (PVC, Flexible)	
Processing Method	Extrusion	
	Injection Molding	
Regional Availability	Africa & Middle East	
	Asia Pacific	
	Europe	
	North America	
	South America	
Uses	Furniture	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China